


ABSTRACT

Polymeric composition, its use for the manufacture of objects and objects so obtained

A stabilized polypropylene composition, free or essentially free of any phenolic antioxidant containing:

- a) 100 parts by weight of a propylene polymer,
- b) from 0.005 to 0.1 part by weight of an amine oxide having the structural formula



wherein R' and R'' are groups containing from 1 to 36 carbon atoms, or of a N,N-dialkylhydroxylamine of formula



wherein

R¹ and R² are independent groups of 1 to 36 carbon atoms,

- c) from 0.1 to 0.5 part by weight of a clarifying agent, and optionally
- d) from 0.01 to 0.1 part by weight of a sterically hindered amine.

Manufacture of shaped object by using said composition and manufactured objects so obtained.